

Tribology and Mechanics of Coatings and Surfaces Room Town & Country B - Session MC3-3-FrM

Tribology of Coatings and Surfaces for Industrial Applications III

Moderators: Osman Eryilmaz, Argonne National Laboratory, USA, Volker Weinhacht, Fraunhofer IWS, Germany

8:00am **MC3-3-FrM-1 High-performance ta-C-based coatings for tribological applications deposited by laser-arc technique, Volker Weinhacht [volker.weinhacht@iws.fraunhofer.de], Frank Kaulfuss, Stefan Makowski, Falko Hofmann, Fabian Hürtwig, Martin Zawischa, Fraunhofer IWS, Germany**

INVITED

Tetrahedral amorphous carbon (ta-C) coatings are increasingly used in tribological contacts and can be found in numerous industrial applications due to their wear resistance caused by super hardness in combination with generally low friction. Fraunhofer IWS has developed a deposition technique for stable industrial coating processes for ta-C using a pulsed, laser-triggered arc discharge on graphite cathodes. The laser-arc technique can be combined with plasma filtering to reduce the density of particle-induced defects in the ta-C coatings. In addition to the further development of plasma filter technology, IWS has currently focused on the development of doped ta-C:(X) coatings by using graphite composite cathodes. In this contribution, it will be shown how doping affects the deposition behavior as well as the structure and properties of the grown ta-C:X coatings. Special emphasis is placed on the tribological properties using various engine oils and alternative, environmentally friendly lubricants.

8:40am **MC3-3-FrM-3 The Development of Amorphous-Based Multi-Component Alloys for the Nanocomposite Coatings and their Properties, Kyoung Il Moon [kimoon@kitech.re.kr], Gi hoon Kwon, Hae Won Yoon, Byounggho Choi, Kyong jun An, Korea Institute of Industrial Technology, Republic of Korea; Sung Chul Cha, Hyundai Motor Group-Hyundai Kefico, Republic of Korea**

While modern industries are becoming more sophisticated, diversified, and globalized, they require the development of smart materials with multi-functionality, high mechanical properties, and extreme durability. Also they could be prepared environmentally friendly and energy efficiently. At the same point of view, the smart coating materials capable of simultaneously expressing various mechanical properties or opposite properties such as high hardness with high toughness, high electricity with high corrosion resistance are attracting attention as versatile and useful materials in the future. In particular, there is an urgent need to develop a novel coating material capable of stably maintaining microstructures and mechanical properties in various external environments, unlike conventional coating materials whose properties and structures are easily changed by the same harsh environments. To get these kinds of objects, the coating material with multi-components is essential. But if the materials should be prepared with one phase with multi components, they could have only one properties. So, nano-composites with various phases should be formed to realize the various properties. So, it is necessary to develop a coating layer composed of various components that could be formed various phases and more complex structures with multifunctional properties.

In this study, various single alloy target materials with various compositions based on the Zr-Cu amorphous materials have been prepared by powder metallurgy methods such as atomization, mechanical alloying, and Spark Plasma Sintering (SPS). The various nanocomposite coatings could be prepared by using single alloying targets. The most important property is the composition of the target material could be transferred to the coating layers. The properties of as-prepared nanocomposite coatings will be summarized in this present including the coating's performance under conditions that simulate EV drivetrain environments.

9:20am **MC3-3-FrM-5 Effect of Boriding on the Surface Hardness and Wear Resistance of Low Carbon Steel Fabricated by Wire Arc Additive Manufacturing (WAAM), Abraham Molina-Sanchez [A01363512@tec.mx], Cesar David Resendiz-Calderon, Leonardo Israel Farfan-Cabrera, Christian Ricardo Cuba-Amesquita, Tecnológico de Monterrey, Mexico**

Wire and Arc Additive Manufacturing (WAAM) enables the production of large-scale, geometrically complex components at a significantly lower cost compared to other additive manufacturing (AM) technologies. It offers extensive material availability, including low-carbon steel, which is widely used in mechanical and structural components. However, due to its low

hardness and corrosion resistance compared to other steels, its use is limited in high-demand environments. This study evaluates the effect of boriding on the surface hardness and wear resistance of low-carbon steel fabricated using the WAAM technique. WAAM-built low-carbon steel plates were printed layer by layer to complete 60 layers per sample using ER70S-6 steel wire (0.8 mm diameter). The parameters included a welding voltage of 19.7 V, 67 A current, 5 mm/s travel speed, and a shielding gas of 100% CO₂ supplied at 15 L/min. These samples were subjected to a boriding process wherein a sealed container with Ekabor 2 powder as the boron donor was used, heated at 950°C for 3 hours, and cooled at room temperature. A boride layer with an average thickness of 93.5 ± 32.6 μm composed of FeB and Fe₂B phases was formed, as confirmed by X-ray diffraction (XRD). The adhesion of the boride layer on the as-built (AB) samples was evaluated using a progressive scratch test, and nanoindentation revealed an increase in hardness with no significant changes along the material deposition direction. Dry-sliding tests measured the coefficient of friction (CoF) between AB and borided samples, and a considerable wear volume decrease of 20% was observed with the boride layer, as measured by optical profilometry. These results demonstrate no significant changes along the build direction in phase composition, hardness, or tribological behavior, indicating that boriding is an effective surface treatment for enhancing wear resistance in WAAM-fabricated low-carbon steel.

10:20am **MC3-3-FrM-8 Ultralow Wear, Conductive Plasma-Enhanced Atomic Layer Deposited Metal Nitrides, Brandon Krick [bkrick@eng.famu.fsu.edu], Florida State University, USA**

INVITED

Author Index

Bold page numbers indicate presenter

— A —

An, Kyong jun: MC3-3-FrM-3, 1

— C —

Cha, Sung Chul: MC3-3-FrM-3, 1

Choi, Byounggho: MC3-3-FrM-3, 1

Cuba-Amesquita, Christian Ricardo: MC3-3-FrM-5, 1

— F —

Farfan-Cabrera, Leonardo Israel: MC3-3-FrM-5, 1

— H —

Härtwig, Fabian: MC3-3-FrM-1, 1

Hofmann, Falko: MC3-3-FrM-1, 1

— K —

Kaulfuss, Frank: MC3-3-FrM-1, 1

Krick, Brandon: MC3-3-FrM-8, **1**

Kwon, Gi hoon: MC3-3-FrM-3, 1

— M —

Makowski, Stefan: MC3-3-FrM-1, 1

Molina-Sanchez, Abraham: MC3-3-FrM-5, **1**

Moon, Kyoung Il: MC3-3-FrM-3, **1**

— R —

Resendiz-Calderon, Cesar David: MC3-3-FrM-5, 1

— W —

Weihnacht, Volker: MC3-3-FrM-1, **1**

— Y —

Yoon, Hae Won: MC3-3-FrM-3, 1

— Z —

Zawischa, Martin: MC3-3-FrM-1, 1